

CUPA 14

DESCRIPTION Non-carbonated slate formed by tectonic compression. Dark grey slate with thin laminations and a riven surface.

ORIGIN Quarry Las Fuentes. Benuza (León) Spain. Operating 1985.

PRODUCTION 6.000 t/year

SIZES (CM) 30x20 - 50x25

THICKNESS (MM) 5 - 7.5 - 9

FORMATS



Square



Rectangular



Rhomboid



Bullnose



90° Sawn

SELECTIONS

R EXCELLENCE

H ARDOISIER

NATURAL

HEAVY

CUPA

CUPA 14



TECHNICAL SPECIFICATIONS

European Standard: EN 12326

British Standard: BS 680 PART 2

WATER ABSORPTION	0,21% Code : W1 (< 0,4%)
CONTENTS OF CARBONATE NON CARBONATED	0,27% Fulfill (< 2%)
MOR CHARACTERISTIC	Longitudinal 37 MPA
SO ₂ EXPOSURE TEST	S1
THERMAL CYCLE TEST	T1
FREEZE THAW TEST	Fulfill < 0,4%

INTERNATIONAL CERTIFICATIONS



CUPA PIZARRAS

One University Plaza, Suite 309;
HACKENSACK, NJ - 07601

Phone +1 (201) 880 9370
Fax +1 (201) 880 9372

usa.cupa@cupagroup.com
www.cupapizarras.com

